



RESIN SYSTEM: GP 331



Tg (GLASS TRANSITION TEMPERATURE)

Tg	Compositon
330°F / 167°C	Neat Resin
320°F / 160°C	Laminate

TYPICAL MATERIAL PROPERTIES

TEMPERATURE °F	Tensile Strength Ksi	Tensile Modulus Msi	Flex Strength Ksi	Flex Modulus Msi	Shear Strength psi
72	54.90	3.06	70.70	2.92	4742

LAST MODIFIED: 3/19/17

sales@genplastics.com
713-644-1449

General Plastics & Composites LP
6910 E. Orem Dr.
Houston, TX 77075

www.genplastics.com